



US007732706B1

(12) **United States Patent**
Mardesich

(10) **Patent No.:** **US 7,732,706 B1**
(45) **Date of Patent:** **Jun. 8, 2010**

(54) **SOLAR CELL CIRCUIT AND METHOD FOR MANUFACTURING SOLAR CELLS**

(75) Inventor: **Nick Mardesich**, San Pedro, CA (US)

(73) Assignee: **The United States of America as represented by the Administrator of the National Aeronautics and Space Administration**, Washington, DC (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 758 days.

(Continued)

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **11/229,782**

WO WO-03073517 A * 4/2003

(22) Filed: **Sep. 16, 2005**

(Continued)

Related U.S. Application Data

(60) Provisional application No. 60/610,837, filed on Sep. 17, 2004.

(51) Int. Cl.

H01L 31/00 (2006.01)

H01L 31/075 (2006.01)

H01L 31/04 (2006.01)

(52) **U.S. Cl.** **136/261**; 136/262; 136/249; 136/255; 136/256; 257/458; 257/431; 438/74; 438/81; 438/93

(58) **Field of Classification Search** 136/255, 136/261, 249, 256, 262
See application file for complete search history.

(56) References Cited

U.S. PATENT DOCUMENTS

3,969,746	A *	7/1976	Kendall et al.	136/255
3,997,381	A *	12/1976	Wanlass	438/10
4,404,422	A *	9/1983	Green et al.	136/255
5,223,043	A *	6/1993	Olson et al.	136/249
5,405,453	A *	4/1995	Ho et al.	136/249
5,616,185	A *	4/1997	Kukulka	136/244
5,716,459	A *	2/1998	Chang et al.	136/249
6,162,987	A	12/2000	Murray et al.	136/253
6,225,793	B1 *	5/2001	Dickmann	323/230

Primary Examiner—Alexa D Neckel

Assistant Examiner—Golam Mowla


(74) *Attorney, Agent, or Firm*—Mark Homer

(57)

ABSTRACT

The invention is a novel manufacturing method for making multi-junction solar cell circuits that addresses current problems associated with such circuits by allowing the formation of integral diodes in the cells and allows for a large number of circuits to readily be placed on a single silicon wafer substrate. The standard Ge wafer used as the base for multi-junction solar cells is replaced with a thinner layer of Ge or a II-V semiconductor material on a silicon/silicon dioxide substrate. This allows high-voltage cells with multiple multi-junction circuits to be manufactured on a single wafer, resulting in less array assembly mass and simplified power management.

12 Claims, 5 Drawing Sheets



US 7,732,706 B1

Page 2

U.S. PATENT DOCUMENTS

2002/0106870	A1 *	8/2002	Henley et al.	438/464	2005/0275067	A1 *	12/2005	Atwater et al.	257/616
2002/0117675	A1 *	8/2002	Mascarenhas	257/87	2006/0162767	A1 *	7/2006	Mascarenhas et al.	136/261
2003/0140962	A1 *	7/2003	Sharps et al.	136/249	2007/0137698	A1 *	6/2007	Wanlass et al.	136/261
2004/0132304	A1 *	7/2004	Farrens et al.	438/690					
2004/0214434	A1 *	10/2004	Atwater et al.	438/689					
2005/0183765	A1 *	8/2005	Ho et al.	136/251					

FOREIGN PATENT DOCUMENTS

WO WO-2004-017425 * 2/2004

* cited by examiner

Circuit on Wafer Design




Figure 1

28% Three Junction Cell Design




Figure 2





Figure 3






Figure 5

1

SOLAR CELL CIRCUIT AND METHOD FOR MANUFACTURING SOLAR CELLS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the priority date associated with provisional application 60/610,837, filed on Sep. 17, 2004, entitled III-V Semiconductor on Silicon Wafer-Solar Cell Circuit.

STATEMENT OF GOVERNMENT INTEREST

The invention described hereunder was made in the performance of work under a NASA contract, and is subject to the provisions of Public Law #96-517 (35 U.S.C. 202) in which the Contractor has elected not to retain title.

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates in general to an improved method of manufacturing solar cells that results in an improved solar cells and solar cell arrays, more specifically to manufacturing multiple junction solar cell circuits on a single wafer, and most specifically to manufacturing multiple solar cells in series on a single wafer.

2. Description of the Related Art

Current multi-junction solar cell circuits for space missions employ Ge, GeAs, and/or InP wafer substrates sectioned from single crystal ingots. An alternative method of manufacture of such substrates is to grow the Ge, GeAs, or InP directly on silicon wafers (through a lattice mismatch process) by growing gradient that slowly matches the silicon lattice to the Ge, GeAs, or InP lattice. In order to promote such growth, relatively high temperatures, of between about 425° C. and 900° C., are required, depending upon the chemical compound being grown.

State of the art solar cells are triple junction solar cells, comprising three full junction layers manufactured on single crystal Ge wafers, that require by-pass diodes between each triple junction cell when assembled in series to prevent damage in case of shadowing. After the triple junction solar cells are formed an out-of-plane stress relief loop is arranged between each of the contacts/conductors interconnection on the cells.

In using this technique for manufacture, non-isolated multi-junction solar cells are manufactured on each Ge wafer. The solar cells are subsequently diced into single isolated cells. This is necessary due to the fact that the cells are connected in parallel on the wafer. End user of this technology generally require high voltage arrays resulting in the cells being connected in series, with by-pass diodes. These interconnects (for arranging the cell circuits in series to form a cell array) require a stress-relief loop as well as the diodes placement on or near the cells make arranging multiple cell circuits on a single Ge wafer problematic.

While multi-junction solar cells manufactured using the above described technique have a relatively high efficiency related to commercial, single junction solar cells, several problems related for use in space missions exist.

First, when arranging the cells into a cell array, a large surface area is required due to the economics (cost) of handling parts on a production line. Second, due to the potentially large differential in voltage across an array between cells, there is a tendency for arcing to occur when the arrays are

2

exposed to a space environment. Third, each wafer, having only one solar cell circuit, can only produce voltages of about 2 volts.

Therefore, it is desired to provide a solar cell circuit using a manufacturing technique that will allow for multiple multi-junction circuits to be placed on one lightweight silicon wafer, producing a high voltage, and obviating the potential for arcing across a solar cell circuit array.

SUMMARY OF THE INVENTION

The invention proposed herein comprises a unique manufacturing method that produces multi-junction solar cell circuits that provide significant increases in potential voltages per each wafer and allows integral by-pass diodes to be formed directly into the substrate on which the solar cells are made.

Accordingly, it is an object of this invention to provide an improved method for manufacturing multi-junction solar cell circuits.

It is a further object of this invention to provide a method for manufacturing solar cell circuits that allows multiple multi-junction cells to be formed on a single wafer substrate.

It is yet a further object of this invention to provide a method for manufacturing solar cell circuits that allows the formation of by-pass diodes directly into the wafer substrate of the solar cell circuits.

This invention meets these and other objectives related to improved solar cell circuits by providing a manufacturing method wherein a silicon based wafer substrate is provided. An insulation layer is formed on the silicon based wafer. A planar by-pass diode is formed integral with the silicon based substrate and insulation layer. A single crystal layer of a compound selected from germanium based compounds, III-V or II-IV semiconductor compounds is bonded to the insulation layer using plasma assisted electrostatic bonding. A wafer cleaving technique is then used to remove a portion of the single crystal layer in order to obtain a particular, preferred thickness for the single crystal layer. In one embodiment of the invention, the excess from the single crystal layer that was cleaved may be used as bonding material in another silicon wafer for the next solar cell circuit. Multi-junction layers are formed on the insulation layer to fabricate a multi-junction solar cell circuit.

In the most preferred embodiment of the invention, a plurality of multi-junction solar cell circuits, manufactured via the process described above, are formed in series on a single silicon wafer substrate. Such a design allows for high-voltage capability for each solar cell wafer as well as minimizing the weight of solar cell arrays.

BRIEF DESCRIPTION OF THE DRAWINGS

In the drawings, which are not necessarily to scale, like or corresponding parts are denoted by like or corresponding reference numerals.

FIG. 1 depicts a cut-away side view of two solar cell circuits of the present invention formed on a single silicon substrate wafer.

FIG. 2 depicts a side view of a cleaved transfer layer during manufacture of the present invention.

FIG. 3 depicts a top view of a high voltage solar cell comprising 30 solar cell circuits of the present invention on a single silicon substrate wafer.

FIG. 4 depicts a top view of a high voltage panel layout for a solar cell array employing multiple high voltage solar cells similar to that depicted in FIG. 3.

FIG. 5 is a flow diagram of the process steps for manufacturing solar cell circuits of the present invention.

DESCRIPTION OF PREFERRED EMBODIMENTS

The invention, as embodied herein, comprises a novel manufacturing method for making multi-junction solar cell circuits that addresses current problems associated with such circuits by allowing the formation of integral diodes in the cells and allows for a large number of circuits to readily be placed on a single silicon wafer substrate. The standard Ge wafer used as the base for multi-junction solar cells is replaced with a thinner layer of Ge, III-V or II-IV semiconductor material on a silicon/silicon dioxide substrate, which has about 40% less density than the standard Ge wafer. This allows high-voltage cell circuits with multiple multi-junction cells to be manufactured on a single wafer, resulting in less array assembly mass and simplified power management.

FIG. 1 shows an embodiment of the present invention depicting two triple junction solar cells **100** formed in series on a processed silicon based wafer **102**. As used herein, doping is a process whereby positively or negatively charged atoms relative to the base material are introduced into a layer of material in order to give the layer a positive or negative charge. The material added as a dopant is selected depending upon the average number of electrons of the material/compound of the layer. The material and specific doping process may be selected by one skilled in the art. Preferred doping materials for the materials layers described herein are phosphorus and boron. The amount of doping of each layer may be selected by one skilled in the art depending upon the type of materials and type of multi-junction solar cell being constructed. As used herein,

A blocking diode **104** is formed on an edge **106** of the silicon based wafer **102**. A plurality of by-pass diodes **108** are also formed in the silicon based wafer **102**. These diodes **104**, **108** may be formed by such processes as epitaxial growth or the diffusion of P⁺ or N⁻ dopants into the silicon based substrate **102**. The number of diodes **104**, **108** formed on the silicon based wafer depend upon the number of solar cell circuits **100** desired on a silicon based wafer **102**. The diodes **104**, **108** are integral to the silicon based wafer and have diode contacts **105** that extend above the wafer **102** so that contacts **142**, **144**, described below, may be electrically connected to the diodes **104**, **108**.

An insulating layer **110**, preferably of silicon oxide, is formed on the silicon based wafer **102** by processes known in the art such as oxide growth, epitaxial growth or deposition. The insulating layer **110** thickness should be such that the diode contacts **105** still extend above the insulating layer **110**. A preferred thickness for the insulating layer is about 1000 angstroms. The insulating layer **110** allows for the diodes **104**, **108** to be formed integral with the silicon based wafer **102** and still be operable with other solar cell layers formed above the insulating layer **110**.

A thin transfer layer **112** comprising a highly positive doped germanium based compound, preferably simple Ge, or semiconductor III-V compound, such as GaAs, is formed on the insulating layer **110**. Plasma assisted electrostatic bonding is used to adhere the transfer layer **112** without adhesive to the insulating layer **110**. This process is described in U.S. Pat. No. 6,908,832, which is incorporated by reference herein. In general, the process works as follows. The layers to be bonded are placed in a plasma chamber, mechanically supported and held, in a predetermined environment, depending upon the types of materials being bonded. One of the faces

of the layers is exposed to a plasma. The layer that was exposed to plasma is then released from being held so that it directly bonds with the other layer. This process allows for bonding of the materials without the need for high temperature anneals or the use of organic or inorganic bonding agents, which would damage the integral diodes **104**, **108** formed in the silicon based wafer **102**. The result is a thick, single crystal layer **200** of Ge or a III-V semiconductor material (see FIG. 2).

In order to obtain a thin transfer layer **112** that is the appropriate thickness, approximately 3000 angstroms is preferred, the thick transfer layer **200** is wafer cleaved. One wafer cleaving process that may be employed in the present invention is described in U.S. Pat. No. 6,632,724, which is incorporated herein by reference. In general, the process works as follows. Prior to electrostatic bonding, energetic atoms are introduced through the layer to a selected depth for cleaving and an energy source is directed to the region of the layer to be cleaved. The energy source initiates a control cleaving of the layer at the selected depth. In a preferred embodiment of the invention, the excess portion **202** of the thick transfer layer cleaved **202** to create the thin transfer layer **112** may be bonded to another insulating layer **110** placed in series on a similar silicon based wafer **102**, described in more detail below, in order to minimize process waste.

After the silicon layer **102**/insulating layer **110**/transfer layer **112** is formed as described above, layers forming a multi-junction solar cells are formed using processes known in the art, such as MO-CVD. In a preferred embodiment of the invention, a base layer **114** of positively doped Ge is placed on the transfer layer **112** of highly positive doped Ge and a negatively doped emitter layer **116** of Ge is placed upon the base layer **114**. A tunnel junction **118** is placed upon the emitter layer **116** in order to complete the first junction **120** of the solar cell circuit **100**.

The second junction **122** of the circuit **100** preferably comprises a base layer **126** of positively doped GaAs, an emitter layer **128** of negatively doped GaAs, and a tunnel junction layer **130**. The third junction **132** comprises a base layer **134** of positively doped GaInP, an emitter layer **136** of negatively doped GaInP, and a window layer **138** of negatively doped AlInGaP. These materials are preferred for the junction layers because of lattice matching between Ge and GaAs and between GaAs and GaInP.

An anti-reflective coating **140** is placed upon the window layer **138** in order to provide enhanced spectral response and a cap layer **141** is placed between the contacts **142** and the window layer **138**. The cap layer **141** is preferably constructed of n⁺ GaAs. A number of etch back process are preformed to remove all the formed layers down to the transfer layer **112**, SiO₂ layer **100** and diode **108**. This process defines the boundary of the cell and exposes the contact area. A positive contact **105** is placed adjacent to the diode contact **108**. An isolation layer is then formed on the edge from the cap layer **141** to the transfer layer **112** on one edge. A negative contact **142** is placed on an edge **146** over the isolation layer of the solar cell circuit **100** that extends to the location of the by-pass diode **108**. The contacts **142**, **144** are electrically connected with the diode in order to prevent damage related to shadowing. The contacts **142**, **144** are constructed of a material that may be selected by one skilled in the art. One material example is chromium/palladium/silver.

Referring to FIGS. 1 and 3, in a preferred embodiment of the invention, a plurality of cell circuits **100** are arranged monolithically in series on a single silicon based wafer in order to construct a high-voltage solar cell **300**. As described

above, the diodes **104**, **108** are arranged across the silicon based wafer **102** and a plurality of solar cell circuits **100** are manufactured between the diodes **104**, **108** so that the by-pass diode contacts **105** abut an edge **146** of the insulating layers **110** and the bottom transfer layers **112**. Solar cell circuits **100** are then manufactured as described above between each pair of diodes **104**, **108**.

A Monolithic Interconnected Module (MIM) structure is formed using semiconductor etch-back and contact formation processes that has been employed to construct thermophotovoltaic (TPV) MIM structures in order to connect the plurality of solar cell circuits **100** on a single wafer **102**. A MIM consists of multiple series of interconnected cells on a common semi-insulating substrate that results in a higher voltage and lower current device and normally incorporates a back surface reflector for optical recuperation for TPVs. There are generally two types of MIM designs currently employed. The first utilizes a highly doped, thick lateral conduction layer (LCL) to conduct the entire length of a cell. The second uses a thinner, lower-doped LCL because the current must flow only a short distance to the nearest grid finger. The second type of MIM design would be employed in the present invention. This arrangement provides for both positive and negative contacts **142**, **144** to be formed on the top of the cell **300**. An example of MIM fabrication can be found in U.S. Pat. No. 6,162,987 which is incorporated by reference herein.

Employing a standard size silicon based wafer **102** (about 4.0 inch diameter) and employing the present invention manufacturing method, approximately 29 or 30 solar cell circuits **100** may be placed on a single wafer **102**. If one selects to add 30 circuits **100** on a wafer **102** the positive contact for the cell **300** will be positioned with the positive contact **302** in the upper left hand corner (and diagonal) and the negative contact **304** in the upper right hand corner (and diagonal) when viewing the cell **300** from above as depicted in FIG. 3. If 29 circuits **100** are selected, the positive contacts **302** are positioned in the upper right and left hand corners of the cell and the negative contacts **304** are positioned in the lower right and left hand corners.

This cell **300** design provides for a high-voltage cell providing 29 or 30 times the voltage compared to a standard multi-junction solar cell. This is due to the fact that each solar cell circuit normally provides about 2 volts. In a standard cell, only one complete circuit is manufactured per wafer. Therefore, a standard cell can only provide about 2 volts of current. However, since the present manufacturing method allows one to place up to 30 circuits **100** on a single wafer, about 60 volts of current can be obtained. This process is not limited to wafer size, larger standard silicon wafers can be employed to create more circuits per wafer and higher voltage circuits.

Referring to FIG. 4, a solar cell array panel layout is depicted using solar cells **300**. Cell panels **300** are placed with the positive contacts **302** arrayed to a conjoining cell's negative contacts **304**. Between the positive and negative contacts **302**, **304** of each cell **300**, as noted above, about 60 volts of current may be provided. Across each cell in the other direction, only about 2 volts of potential exist. Therefore, the maximum potential voltage from any edge of one cell to another in the array is about 5 volts. This potential voltage is too low to cause arcing, as described above. The design further allows for a coverglass **400** to be placed over each cell **300** in order to provide protection for the cells **300**.

Referring to FIG. 5, a flow diagram depicting the major steps of the manufacturing method used to practice the present invention is provided. A standard sized silicon based wafer is provided **500**. Next, a plurality of diodes are formed integral in the silicon based wafer **510**. In this step, diode

connectors extend to the surface of the silicon based wafer. Third, a silicon oxide insulation layer is formed on the silicon based wafer **520**. The preferred insulation layer thickness is about 1000 angstroms so that the diode connectors can be exposed by silicon oxide etch back. Fourth, a thick, single crystal layer of either a germanium based compound, III-V or a II-IV semiconductor compound, prepared with energetic atoms, is bonded to the insulation layer **530**. Plasma assisted electrostatic bonding is used to bond the single crystal layer to the insulating layer. Next, a wafer cleaving process, employing the energetic atoms within the single crystal layer, is used to cleave a portion of the single crystal layer to provide a selected thickness for the single crystal layer of about 3000 angstroms **540**. Preferably, the excess single crystal layer from the cleaving process is used to form the next in a series of single crystal layers between the plurality of diodes **550**. After the cleaving step, multi-junction layers for a solar cell circuit are formed using processes known in the art **560**. The wafer is back etched to expose the plurality of multi-junction solar cell layers on the silicon based wafer. Contacts are formed between the transfer layer **112** and diode **105**. An isolating layer is then formed on the edge of the layers. Finally, a monolithic interconnected structure is formed to electrically interconnect the negative contacts that are formed on each of the multi-junction solar cell layers circuits to each circuits' diode **570**.

What is described are specific examples of many possible variations on the same invention and are not intended in a limiting sense. The claimed invention can be practiced using other variations not specifically described above.

What is claimed is:

1. A method of making a solar cell circuit, comprising the steps of:
 - providing a silicon wafer;
 - forming an insulation layer directly on the silicon wafer;
 - bonding a single crystal layer of a compound selected from germanium based compounds, II-IV semiconductor compounds, or III-V semiconductor compounds using plasma assisted electrostatic bonding directly to the insulation layer;
 - wafer cleaving the single crystal layer to obtain a crystal layer of desired thickness and an excess layer; and,
 - forming multi-junction layers on the insulation layer to fabricate a multi-junction solar cell circuit.
2. The method of claim 1, wherein the insulation layer comprises silicon oxide.
3. The method of claim 2, further comprising the step of:
 - forming a plurality of planar by-pass diodes integral with the silicon wafer and the insulation layer before the bonding step; and,
 - forming a plurality of multi-junction solar cell circuits between the planar by-pass diodes.
4. The method of claim 3, wherein the forming a plurality of planar by-pass diodes step is selected from the group of epitaxial growth of the diode into the insulation layer and diffusion of P⁺ and N⁻ dopants into the silicon wafer.
5. The method of claim 3, further comprising the step of forming a monolithic interconnected module structure to electronically interconnect the plurality of multi-junction solar cell circuits on the silicon wafer through positive contacts and negative contacts electronically connected with the by-pass diodes.
6. The method of claim 5 wherein the planar by-pass diodes comprise a position at an edge of each of the plurality of multi-junction solar cell circuits.
7. The method of claim 6, further comprising the step of forming a blocking diode on an edge opposite of the planar

7

by-pass diode on a first multi-junction solar cell circuit in the plurality of multi-junction solar cell circuits.

8. The method of claim **7**, wherein the multi-junction solar cell circuit comprises a triple junction.

9. The method of claim **8**, further comprising the step of using the excess layer for manufacture of another of the plurality of solar cell circuits. 5

10. The method of claim **9**, wherein the triple junction solar cell circuit comprises a first junction having base and emitter layers comprising Ge.

8

11. The method of claim **10**, wherein the triple junction solar cell circuit comprises a second junction having base and emitter layers comprising GaAs.

12. The method of claim **11**, wherein the triple junction solar cell circuit comprises a third junction having base and emitter layers comprising GaInP.

* * * * *